



DESCRIPTION

- a two pack polyamide cured epoxy high build zinc phosphate primer
- approved to APAS 2971
- conforms to AS/NZS 3750.13

PRINCIPAL CHARACTERISTICS

- general purpose anticorrosive primer specifically for use on steel
- excellent adhesion to steel
- excellent flow and wetting properties
- excellent corrosion resistance
- cures at temperatures down to +5°C
- suitable for touching up of weld seams and damages of epoxy coatings during construction
- long recoating intervals are possible when overcoating with epoxy and polyurethane coatings
- can be overcoated with most alkyd, chlorinated rubber, epoxy, two component polyurethane and catalysed acrylic coatings
- not suitable for immersion
- not suitable for use on non ferrous substrates e.g. aluminium, galvanised steel, ZINCALUME[®]
- cure with EpinameI EH100 standard hardener or EpinameI EH120 low temperature hardener

COLOURS AND GLOSS

- Grey - semi gloss

BASIC DATA AT 25°C

- solids content approx. 55% by volume
- mix ratio 4A:1B by volume
- typical film thickness (per coat) 75 - 200 microns(dry), 135 - 365 microns(wet), depending on coating system
- theoretical spreading rate 7.3 m²/l for 75 microns(dry), 2.8 m²/l for 200 microns(dry)
- touch dry after..... 1 - 2 hours (EpinameI EH100)
- overcoating..... refer to overcoating table for details
- full cure after..... 7 days (EpinameI EH100), 3 days (EpinameI EH120)
- shelf life (cool and dry place)..... at least 12 months

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- all surfaces to be coated must be clean, dry and free from chalking and contamination
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning
- mild steel; blast clean in accordance with AS 1627.4 to Sa 2 ½ minimum (As 1627.9), surface profile 40-70 microns
- if oxidation occurs between blasting and application, the surface should be reblasted to the specified visual standard
- surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner
- mild steel; power tool clean in accordance with AS 1627.2 to St 2 minimum (AS 1627.9)
- steel, wet blast clean to achieve a surface similar to Sa 2 ½ (AS 1627.9), profile 35-50 um
- previous suitable coat; dry and free from any contamination and sufficiently roughened if necessary
- substrate temperature must be at least 5°C during surface preparation, application and curing and at least 3°C above dew point



INSTRUCTIONS FOR USE

- mixing ratio by volume: 4A:1B
- mix with EpinameL EH100 standard hardener or EpinameL EH120 low temperature hardener
- induction time - none
- pot life at 25°C - 6 hours (EpinameL EH100). Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- for recommendations outside those contained in this data sheet, refer to WattyL

APPLICATION

- **AIRLESS SPRAY**
 - recommended thinner Thinner L760
 - volume of thinner up to 5%
 - nozzle orifice..... approx. 0.46 mm (0.018 inch)
 - nozzle pressure 15 MPa (2100 psi)
- **AIR SPRAY**
 - recommended thinner Thinner L760
 - volume of thinner up to 15%
 - nozzle orifice..... 1.5-2mm
 - nozzle pressure 0.3-0.4 MPa (50 - 60 psi)
- **BRUSH/ROLLER**
 - recommended thinner Thinner L760
 - volume of thinner up to 5%
 - The maximum dry film thickness that can be achieved when brushing/rolling is 50 microns
 - Multiple coats may be required to achieve the recommended dry film thickness
- **CLEANING SOLVENT** Thinner L760

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

**ADDITIONAL DATA****Overcoating table - with two pack epoxy, polyurethane coatings**

Substrate temperature	Epinamel EH100				Epinamel EH120			
	5°C	15°C	25°C	35°C	5°C	15°C	25°C	35°C
Minimum interval	36 hrs	10 hrs	8 hrs	6 hrs	2 hrs	1½ hrs	1 hr	30 min
Max interval when NOT exposed to direct sunlight	6 mth	6 mth	6 mth	4 mth	1 mth	1 mth	1 mth	16 days
Maximum interval when exposed to direct sunlight	3 mth	3 mth	3 mth	2 mth	16 days	16 days	16 days	7 days

- surface must be dry and free from chalking and contamination

Overcoating table - with chlorinated rubber, alkyd and catalysed acrylic coatings

Substrate temperature	Epinamel EH100			
	5°C	15°C	25°C	35°C
Minimum interval	16 hrs	6 hrs	5 hrs	3 hrs
Maximum interval	21 days	14 days	10 days	5 days

- surface must be dry and free from chalking and contamination

Curing table

Substrate temperature	Epinamel EH100			Epinamel EH120		
	Touch dry	Dry to handle	Full cure	Touch dry	Dry to handle	Full cure
5°C	5 hrs	6 hrs	21 days	2 hrs	3 hrs	9 days
15°C	2½ hrs	3 hrs	10 days	1½ hrs	2 hrs	5 days
25°C	1½ hrs	2 hrs	7 days	45 min	1 hr	3 days
35°C	45 min	1 hr	5 days	30 min	45 min	2 days

- adequate ventilation must be continuously maintained during application and curing

Pot life (at application viscosity)

Paint temperature	Epinamel EH100	Epinamel EH120
15°C	10 hrs	6 hrs
25°C	6 hrs	3 hrs
35°C	3 hrs	1½ hrs

CUSTOMER SERVICE HOTLINE 132101 (Aust)

Wattyl® and Epiname® are registered trademarks of Wattyl Australia Pty Ltd.
ZINCALUME® is a registered trademark of Bluescope Steel Limited.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office. 4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.
WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)