

**DESCRIPTION**

- a universal two pack adhesion promoting, polyamide cured epoxy primer
- approved to APAS-2971
- conforms to AS/NZS 3750.13 Type 2 and 3
- FDA Food Contact Compliant (refer below)

**PRINCIPAL CHARACTERISTICS**

- general purpose epoxy primer in protective coating systems for steel and non ferrous metals
- excellent adhesion to steel, galvanized steel, non ferrous metals and fibreglass
- excellent flow and wetting properties
- excellent water and corrosion resistance
- cures at temperatures down to +5°C
- suitable for touching up of weld seams and damages of epoxy coatings during construction
- long recoating intervals are possible when overcoating with epoxy and polyurethane coatings
- can be overcoated with most alkyd, chlorinated rubber, epoxy, two component polyurethane and catalysed acrylic coatings
- suitable on wet blast cleaned substrates (damp or dry)
- suitable primer for immersion systems (in fresh and salt water) when applied over suitably prepared surfaces
- suitable with well designed cathodic protection systems
- suitable for use as a prefabrication primer (refer to technical data sheet P30.07 for details)
- cure with EpinameL EH100 standard hardener or EpinameL EH120 low temperature hardener

**COLOURS AND GLOSS**

- Olive Green, Off-White - semi gloss

**BASIC DATA AT 25°C**

- solids content ..... approx. 55% by volume
- mix ratio ..... 4A:1B by volume
- typical film thickness (per coat) ..... 75 - 200 microns(dry), 135 - 365 microns(wet), depending on coating system
- theoretical spreading rate ..... 7.3 m<sup>2</sup>/l for 75 microns(dry), 2.8 m<sup>2</sup>/l for 200 microns(dry)
- touch dry after ..... 1 - 2 hours (EpinameL EH100)
- overcoating ..... refer to overcoating table for details
- full cure after ..... 7 days (EpinameL EH100), 3 days (EpinameL EH120)
- shelf life (cool and dry place) ..... at least 12 months

**RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE**

- all surfaces to be coated must be clean and free from chalking and contamination
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning
- mild steel; blast clean in accordance with AS 1627.4 to Sa 2½ minimum (AS 1627.9), surface profile 40-70 microns
- if oxidation occurs between blasting and application, the surface should be reblasted to the specified visual standard
- surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner
- mild steel; power tool clean in accordance with AS 1627.2 to St 2 minimum (AS 1627.9), (atmospheric exposure only)
- mild steel; wet blast clean to achieve a surface similar to Sa 2½ (AS 1627.9), profile 35-50 µm (atmospheric exposure only)



- galvanised steel; lightly blast using an inert grit or power tool clean to achieve a roughened uniform flat appearance
- aluminium; lightly blast clean using an inert grit and achieve a surface profile of 35-50 microns
- aluminium; mechanically abrade using 80 grit paper/disc
- stainless steel; blast clean using an inert grit and achieve a surface profile of 35-50 microns
- stainless steel; mechanically abrade using 80 grit paper/disc
- fibreglass; mechanically abrade using 120 grit paper/disc
- ZINCALUME® or COLORBOND®; lightly sand the surface
- hot metal spray; high pressure water wash
- previous suitable coat; dry and free from any contamination and sufficiently roughened if necessary
- substrate temperature must be at least 5°C during surface preparation, application and curing and at least 3°C above dew point

### INSTRUCTIONS FOR USE

- mixing ratio by volume: 4A : 1B
- mix with Epiname EH100 standard hardener or Epiname EH120 low temperature hardener only
- induction time - none
- pot life at 25°C - 6 hours (Epiname EH100). Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- Watty recommends the use of coating inspection reports in compliance with AS/NZS 3893.10,11,12 refer to Information Sheet I-20 for more information
- for recommendations outside those contained in this data sheet, refer to Watty

### APPLICATION

- **AIRLESS SPRAY**
  - recommended thinner ..... Thinner L760
  - volume of thinner..... up to 5%
  - nozzle orifice..... approx. 0.46 mm (0.018 inch)
  - nozzle pressure ..... 15 MPa (2100 psi)
- **AIR SPRAY**
  - recommended thinner ..... Thinner L760
  - volume of thinner..... up to 15%
  - nozzle orifice..... 1.8-2.0mm
  - nozzle pressure ..... 0.3 - 0.4 MPa (50 - 60 psi)
- **BRUSH/ROLLER**
  - recommended thinner ..... Thinner L760
  - volume of thinner..... up to 5%

The maximum dry film thickness that can be achieved when brushing/rolling is 50 microns  
Multiple coats may be required to achieve the recommended dry film thickness
- **CLEANING SOLVENT** ..... Thinner L760



**SAFETY PRECAUTIONS**

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

**ADDITIONAL DATA**

**Overcoating table - with two pack epoxy, polyurethane coatings**

Substrate temperature	Epinamel EH100				Epinamel EH120			
	5°C	15°C	25°C	35°C	5°C	15°C	25°C	35°C
Minimum interval	36 hrs	10 hrs	8 hrs	6 hrs	8 hrs	5 hrs	3 hr	2 hrs
Max interval when NOT exposed to direct sunlight	6 mth	6 mth	6 mth	4 mth	1 mth	1 mth	1 mth	14 days
Maximum interval when exposed to direct sunlight	3 mth	3 mth	3 mth	2 mth	14 days	14 days	14 days	7 days

- when using EpinameL EH120 for immersion applications the minimum overcoating times applicable for EpinameL EH100 must be observed

**Overcoating table - with chlorinated rubber, alkyd and catalysed acrylic coatings**

Substrate temperature	Epinamel EH100				Epinamel EH120			
	5°C	15°C	25°C	35°C	5°C	15°C	25°C	35°C
Minimum interval	16 hrs	6 hrs	5 hrs	3 hrs	6 hrs	4 hrs	2 hrs	1 hr
Maximum interval	21 days	14 days	10 days	5 days	10 days	7 days	5 days	3 days

Note: surface must be dry and free from chalking and contamination prior to overcoating. If overcoating interval is exceeded, the surface must be dry and free from chalking and contamination and sufficiently roughened.

**Curing table**

Substrate temperature	Epinamel EH100			Epinamel EH120		
	Touch dry	Dry to handle	Full cure	Touch dry	Dry to handle	Full cure
5°C	5 hrs	6 hrs	21 days	2 hrs	3 hrs	9 days
15°C	2½ hrs	3 hrs	10 days	1½ hrs	2 hrs	5 days
25°C	1½ hrs	2 hrs	7 days	45 min	1 hr	3 days
35°C	45 min	1 hr	5 days	30 min	45 min	2 days

- adequate ventilation must be continuously maintained during application and curing

**Pot life (at application viscosity)**

Paint temperature	Epiname1 EH100	Epiname1 EH120
15°C	10 hrs	6 hrs
25°C	6 hrs	3 hrs
35°C	3 hrs	1½ hr

**FOOD APPROVAL**

- The film forming components of Epiname1 PR250 are allowed by the Food and Drug Authority (FDA), U.S. Code of Federal Regulation, Section 175.300 for use in food processing environments in contact with dry food stuffs. The film shall be fully cured prior to exposure and is subject to the limitations and conditions of use prescribed in the above Section. For use in other food contact environments please contact Watty1 Technical Services for advice.

For the most up to date information contact Watty1 Customer Service Hotline or visit the Watty1 Website.

CUSTOMER SERVICE HOTLINE  
WEBSITE

Australia  
132 101  
<http://www.watty1.com.au>

New Zealand  
0800 735 551  
<http://www.watty1.co.nz>

Watty1 and Epiname1 are registered trademarks of Watty1 Australia Pty Ltd.  
ZINCALUME<sup>®</sup> and COLORBOND<sup>®</sup> are registered trademarks of Bluescope Steel Limited.

1. This information is important to ensure that the listed Watty1 product(s) perform according to the stated application and uses and must be followed to meet Watty1's warranties express and implied. Watty1 advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Watty1 and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Watty1 endeavours to update this information and maintain the accuracy and currency of its contents, Watty1 does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Watty1 recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty1 office before using the product(s). 4. To the full extent permitted by law, Watty1's liability for breach of a condition or warranty implied into the contract for sale between Watty1 and you by law is limited at Watty1's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Watty1 Technical Services shall be contacted prior to commencement. WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)